

# SECTION-IVE

## EMPLOYER DESIGN FOUNDATIONS

**(Applicable for Transmission Lines  
wherein Foundation Design is in  
Employer's scope)**

TECHNICAL SPECIFICATIONS

SECTION-IV E

EMPLOYER DESIGN FOUNDATIONS

Revision History

Revision No.	Date	Clause Ref	Description
Rev-0	June'2021		First Release
Rev-1	Sept'2021		First Revision
Rev-2	Jan'2022		Second Revision
Rev-3	Oct'2022		Third Revision
Rev-4	Mar'2023		Fourth Revision
Rev-5	Dec'2023		Fifth Revision

TECHNICAL SPECIFICATIONS

SECTION-IV E

EMPLOYER DESIGN FOUNDATIONS

CONTENTS

Clause No.	Description	Page No.
1.1	Foundations	1
1.2	Type of Foundations	1
1.3	Classifications of Foundations	1
1.4	Design of Foundations	3
1.5	Soil Investigation	4
1.6	Properties of concrete	4
1.7	Construction of Tower Foundation, Stub Setting and Earthing	6
1.8	Unit Rates and Measurement for Foundation	8
1.9	Setting of Stubs	9
1.10	Mixing, Placing and Compacting of Concrete	10
1.11	Curing	12
1.12	Backfilling and Removal of Stub Templates	12
1.13	Benching	13
1.14	Protection of Tower and Tower Footing	13

## TECHNICAL SPECIFICATIONS

### SECTION- IV E

#### EMPLOYER DESIGN FOUNDATIONS

#### 1.1 Foundations

Foundation includes supply of all labour, tools & machineries, materials such as cement, sand, coarse aggregates and reinforcement steel and all associated activities, such as, excavation, concreting and back filling etc.

#### 1.2 Type of Foundations

The foundation shall generally be of open cast type. Plain Cement Concrete/ Reinforced Cement Concrete footing shall be used for all type of normal towers. All the four footings of the tower and their extensions shall be similar for a particular location, except where soil condition and or water table are different at different legs. The total depth of foundation, below ground level shall be upto 3.5 meters. For Hard Rock type and also where specific site conditions/ properties demand foundation of different depths (lower or higher), the same shall be adopted. Minimum reinforcement as 0.12% of cross section area shall be provided in raft/ block of hard rock foundation. The raft/ block shall also satisfy the design criteria as per IS 456.

Further, for multi-circuit tower foundations, the foundation depth shall be 3.5 meters and for river crossing open cast foundations, the foundation depth shall be more than 3.5 meters.

#### 1.3 Classifications of Foundations:

The foundation designs shall depend upon the type of soil, sub soil water level and the presence of surface water which have been classified as follows (except pile foundations which is described in relevant section of this specification).

##### 1.3.1 Normal Dry

To be used for locations where normal dry cohesive or non-cohesive soils are met. Foundations in areas where surface water encountered from rain runoff shall also be classified as normal dry.

##### 1.3.2 Sandy Dry Soil

To be used for locations where cohesion less pure sand or sand with clay content less than 10% met in dry condition. If the clay content is more than 10% met in dry condition, the foundation shall be classified as Normal Dry.

1.3.3 **Wet**

To be used for locations where sub-soil water table is met between 1.5 meters from ground level and the depth of foundation below the ground level.

1.3.4 **Wet Cultivated**

To be used for locations where there is no sub-soil water within the foundation depth but which are in surface water for long period with water penetration not exceeding one meter below the ground level e.g. paddy fields/ cultivated field. However, if water penetration due to surface water is more than one meter below ground level, the adoption of suitable foundation shall be decided by site-in-charge in consultation with Corporate engineering Department

1.3.5 **Partially Submerged**

To be used at locations where sub-soil water table is met between 0.75 meter and 1.5 meter below the ground level.

1.3.6 **Fully Submerged**

To be used at locations where sub-soil water table is met at less than 0.75 meter below the ground level.

1.3.7 **Black Cotton Soil**

To be used at locations where soil is clay type, not necessarily black in colour, which shrinks when dry and swells when wet, resulting in differential movement. For designing foundations, for such locations, the soil is considered submerged in nature.

1.3.8 **Fissured Rock**

To be used at locations where decomposed or fissured rock, hard gravel, kankar, limestone, laterite or any other soil of similar nature is met. Under cut type foundation is to be used for fissured rock locations.

In case of fissured rock locations, where water table is met at 1.5M or more below ground level, wet fissured rock foundations shall be adopted. Where fissured rock is encountered with subsoil water table less than 1.5 meter below ground level, submerged fissured rock foundations shall be adopted. In case of dry locations dry fissured rock foundations shall be adopted.

1.3.9 **Hard Rock**

The locations where chiseling, drilling and blasting is required for excavation for monolithic rock for a particular leg/ tower, Hard rock type foundations are to be used. For these locations rock anchoring is to be provided to resist uplift forces.

- 1.3.10 The sub-soil water table is not constant and its level changes during different seasons due to various factors. In case during soil investigation/ trial pit or during excavation, if wet soil/ fissures rock is encountered within the foundation depth, it is to be considered that water table has been encountered (considering that water table had reached that level sometime in past) and accordingly type of foundation shall be classified.
- 1.3.11 Where soil is of composite in nature, classification of foundation shall be according to the type of soil predominant in the foundation pit.
- 1.3.12 The foundation classification at any particular location shall be based on the type of soil (clay/ sandy/ silt/ fissured rock etc.) and water table, presence of surface water, etc. at the location. However, in case of locations which are in vicinity of rivers, depending upon case to case, type of foundation is to be decided considering other aspects also e.g. in case RL (reduced level) of a location in comparison to the HFL is lower and there is possibility of submergence at the time of floods due to absence of river bunds/ protection etc., FS type foundation with suitable raised chimney is to be adopted. Further in case there is a possibility of change in river course, considering the nature and turbulence of probable water flow and subsequent scouring of soil, pile type or special foundation may be considered for these locations.

#### 1.4 Design of Foundations

- 1.4.1 Design of foundations as classified under *Clause 1.3* for all towers and towers with extensions shall be developed by the Employer based on the standard soil properties. The indicative shape of foundation is also enclosed in this specification.
- 1.4.2 In case of normal foundation, minimum clearance between chimney concrete level and ground level shall be 225 mm. Based on specific site condition to avoid rusting of stubs, foundation with 500 mm clearance between concrete level and ground level may be used on case to case basis as may decide by Site-In-charge.
- 1.4.3 Depending on the site conditions other types of foundations shall also be designed and provided by the Employer suitable for Intermediate conditions under the above classifications to affect more economy or to suit specific site conditions encountered.

The proposal for these types of foundations shall be submitted by the Contractor based on the detailed soil investigation and duly recommended by Engineer-in-charge.

- 1.4.4 The construction drawings/ working drawings of all type of foundations classified as in **Clause 1.3** shall be provided to the contractor progressively during execution stage. The drawings for other foundations designed for specific site conditions shall be provided based on actual site requirements only.
- 1.4.5 The special foundations like pile foundations and combined raft foundation if required shall also be designed by the Employer based on detailed soil investigation report. The working drawing of these foundations shall be provided by the Employer to the Contractor during execution stage based on requirements. For detailed specification for pile foundations relevant section of this specification shall apply.
- 1.4.6 The provisional quantities of excavation, concreting and reinforcement steel required for the project are furnished in the BPS.

## 1.5 Soil Investigation

The Contractor may be required to undertake soil investigation as per clause 4.0 of Section-III at some tower locations as required by the Employer. The bearing capacity of soil is to be derived from both shear and settlement criteria. The total permissible settlement of soil may be considered as 50 mm in case of suspension towers and 40 mm in case of tension towers for determining bearing capacity of soil from settlement criteria. The provisional numbers of soil testing locations are furnished in BPS. However, contractor shall take reference to the soil investigations wherever already carried out by the Employer.

## 1.6 Properties of Concrete

### 1.6.1 For open cast type foundation

The cement concrete used for the foundations shall generally be of grade M20 having 1:1.5:3 nominal volumetric mix ratio with 20 mm coarse aggregate graded downward for chimney portion and pyramid or slab portion. All the properties of concrete regarding its strength under compression, tension, shear, punching and bending etc. as well as workmanship will conform to IS 456.

Weigh batching in place of volumetric batching (1:1.5:3) as an alternative may be adopted. Further, use of self loaders viz Ajax Fiori / small portable weigh batcher may be permitted for batching and mixing of concrete, subjected to compliance of following: -

- (i) Weight of cement, sand and aggregate equivalent to that of nominal mix of proportion 1:1.5:3 by volume basis shall be calculated. For finalisation of weight, average of 5 samples of cement, sand and aggregates shall be taken from measurement boxes. The volumetric conversions to the weight shall be noted and the same conversion shall be applied to the entire location.
- (ii) For every change in source of sand/ aggregates, the weights shall be recorded.
- (iii) The minimum cement content shall remain same i.e. 400 kg/m<sup>3</sup>.

- (iv) Calibration certificate of self-loader/concrete producing equipment shall be checked before start of concreting works. The accuracy of the measuring equipment shall be within +/- 2% of the quantity of cement and within +/-3% of the quantity of aggregate.
- (v) Preferably, print out of each load indicating weight of all the constituent's material i.e. Cement, Fine Aggregate, Coarse Aggregate, Water, Admixture (If any) is to be ensured or proper records shall be maintained to ensure weight of constituents materials.
- (vi) Necessary modification in weight of fine aggregate due to bulkage may be taken care in weigh batching. Water cement ration due to moisture content shall be suitably adjusted.
- (vii) Concreting using RMC (Ready Mix Concrete) may also be carried out with weight ratio to be calculated as per S.No. (i) above.

1.6.2.1 The Quantity of minimum cement to be used per unit quantity of consumption for different mix (nominal mix) of concrete should be as follows:

Sl. No.	Description	Unit	Quantity of Minimum cement to be used per Unit quantity of work (in kg)
1.	1:1.5:3 nominal mix concrete	cum	400
2.	1:2:4 nominal mix concrete	cum	320
3.	1:3:6 nominal mix concrete	cum	220
4.	Random Rubble Masonry with 1:6 cement mortar	cum	83

In this regard utilisation record is to be maintained at site.

1.6.2.2 Alternatively, ready-mix concrete from batching plant as per IS 4925 can also be used with no extra payment and without any recovery. However, cement content shall be as per IS 456, unless otherwise specified herein. The ready-mix concrete shall conform to IS 4926. The selection and use of Materials for the ready-mix concrete shall be in accordance with IS 456. The concrete shall be of M25 grade design mix as per IS 456. The transport of concrete and transportation time shall be as per IS 4926.

1.6.2.3 Ready-mix concrete of M25 grade design mix as per IS 456, shall be used for foundations of railway crossing locations.

1.6.2.4 Use of small batching machines/ self-loading mixers may be allowed after verification of cement consumption and mix by Employer site-in-charge. The equipment shall have facility of checking the proportion of ingredients of concrete being made. The records of mix shall be maintained at site. The calibration of equipment shall be done at regular intervals.

1.6.2.5 Ready mix concrete of M25 grade shall be designed as per IS 456. However, minimum cement content shall not be less than 330 kg/m<sup>3</sup>.

1.6.3 Cement used shall be ordinary Portland Cement, unless mentioned otherwise, conforming to the latest Indian Standard Code IS 269 or IS 8112 or IS 12269.

Alternatively, other varieties of cement other than ordinary Portland Cement such as Portland Pozzolana Cement conforming to IS 1489 (latest edition) or Portland Slag Cement conforming to IS 455 (Latest edition) can also be used. The Contractor shall submit the manufacturer's certificate, for each consignment of cement procured, to the Employer. However, Employer reserves the right to direct the Contractor to conduct tests for each batch/ lot of cement used by the Contractor and Contractor will conduct those tests free of cost at the laboratory so directed by the Employer. The Contractor shall also have no claim towards suspension of work due to time taken in conducting tests in the laboratory. Changing of brand or type of cement within the same structure shall not be permitted without the prior approval of the Employer. Sulphate Resistant Cement shall be used if Sulphate content is more than the limits specified in IS 456, as per Geotechnical investigation report.

Ordinary Portland Cement (OPC) and Portland Pozzolana Cement (PPC) or Portland Slag Cement are Technically Equivalent and there would not be any financial implication/ or recovery to be borne by Employer/ Contractor. However, the minimum cement content shall be as per above table for nominal mix concrete.

1.6.4 Coarse and fine aggregates shall confirm to IS 383.

1.6.5 The water used for mixing concrete shall be fresh, clean and free from oil, acids & alkalis, organic materials or other deleterious substances.

1.6.6 Reinforcement shall confirm to IS 1786 for high strength steel bars (Fe 500/ Fe500D/ Fe 550 / Fe 550D). If mentioned in BPS, epoxy coated reinforcement conforming to IS 13620 shall be used. Thermo Mechanically Treated (TMT) bars (equivalent grade) in place of cold twisted bars are also accepted. Hard drawn steel wire shall conform to IS 432. All reinforcement shall be clean and free from loose mill scales, dust, loose rust and coats of paint, oil or other coatings, which may destroy or reduce bond. Contractor shall supply, fabricate and place reinforcement to shapes and dimensions as indicated or as required to carry out the intent of approved foundation drawings and Specifications. The contractor may also use pre-fabricated/ assembled reinforcement cage conforming to shape, dimension, size as per approved foundation drawing. Spacers, chairs, stays, hangers, overlaps/couplers, and annealed steel wire for binding etc. as may be necessary, should be used for proper completion of the foundation job as per requirement. Spacers or chairs should be placed at a maximum spacing of 1m and closer spacing shall be provided wherever necessary.

1.6.7 Use of crushed stone in place of natural sand, in case of non-availability or restriction by local authority, may be allowed by Employer site-in-charge subject to sieve analysis meeting acceptance criteria as per relevant IS and complying of other requirement as per standard field quality plan.

1.6.8 For foundation in coastal areas or creek or aggressive soil areas or under marine environment, if mentioned in BPS, Ready Mix Concrete of M30 Grade shall be used to avoid use of locally available saline water. However, design mix concrete of M30 Grade conforming to IS 456 with potable water can be used at locations where transportation of ready-mix concrete is not feasible. Minimum cement content in any case shall not be less than 330kg/m<sup>3</sup>. Plain concrete/lean concrete shall of grade M20 nominal mix 1:1.5:3. The surface of the reinforcement steel shall be treated with epoxy-based coating to enhance corrosion performance of foundation. Use of epoxy coated reinforcement in foundation shall be as per IS 13620. In addition, 02 (two) numbers of coats of bituminous painting of minimum 5 sq. m/litre per coat shall be applied on all the exposed faces of the foundation (i.e. pedestal & base slab). Double coat of total 20 mm thick cement plaster shall be provided on all exposed concrete surface as well upto 300 mm below ground level to give protection to concrete surface from environmental and saline effect. Before coping of chimney top portion, three coats of anti-corrosive paint of minimum 30-35 microns dry film thickness each shall be applied on the stub in the 50 mm coping portion as well as upto 350mm above CL portion. Cost of the above shall be deemed to be included in the unit rate of M30 concrete.

Corrosion resistant steel (CRS) of grade Fe500 / Fe 500D / Fe 550 / Fe 550D conforming to IS 1786 may be adopted as an alternative to epoxy coated reinforcement for foundation in coastal areas or creek or aggressive soil areas or under marine environment.

In case of foundation in coastal areas or creek or aggressive soil areas or under marine environment, Portland Pozzolana Cement (PPC) or Portland Slag Cement shall be used .

## **1.7 Construction of Tower Foundation, Stub Setting and Earthing**

### **1.7.1 Excavation**

1.7.1.1 The excavation work for foundations shall be taken up by the contractor progressively stretch wise/ section wise after obtaining approval from Employer for the proposed stretch wise/ section wise tower schedule, profile etc. as per detailed survey along the approved route alignment.

1.7.1.2 Except as specifically otherwise provided, all excavation for footings shall be made to the lines and grades of the foundations. The excavation wall shall be vertical

and the pit dimensions shall be based on an assumed clearance of 150 mm on all sides of the foundation pad. For footings with undercut, care shall be taken to carry out excavation as per drawing without any side clearance. For Fissured rock foundations, undercut as shown in the drawing is required and shall be provided accordingly. In cases where undercutting portion is excavated beyond stipulated dimension, the extended undercut portion shall be filled with additional concrete and reinforcement shall be extended into the undercut portion considering margin for concrete cover. However, payment of concrete & reinforcement shall be limited to design volumes of excavation, concrete, reinforcement etc. All excavation shall be protected so as to maintain a clean sub grade and provide worker safety until the footing is placed, wherever the soil is loose or collapsible or in case of water in excavated pit, using timbering, shoring, shuttering, dewatering arrangements etc. as approved by the Employer/ Site-In-Charge. Contractor shall especially avoid disturbing the bearing surface of the pad. Any sand, mud, silt or other undesirable materials which may accumulate in the excavated pit or borehole shall be removed by Contractor before placing concrete.

1.7.1.3 Keeping in view of safety aspect, in case any sloped/ stepped/ ramp excavation for easy movement of man and material in excavation pit is required the same shall be done by the contractor. No Extra payment shall be admissible to the Contractor for the same.

1.7.1.4 The soil to be excavated for tower foundations shall be classified as follows depending upon the physical state of the soil at the time of excavation irrespective of the type of foundation installed.

a) **Dry Soil**

Soil removable either manually, by means of a spade and shovel or mechanically by poclains, excavators etc.

Excavation done in dry soil for wet, partially submerged, fully submerged and wet black cotton type of foundations shall also be covered under this.

b) **Wet Soil**

During excavation, if wet soil is encountered within the foundation depth, the type of soil shall be considered as Wet irrespective of whether pumping/ bailing out of water is required or not. The excavation done in wet soil in case of wet, wet cultivated, partially submerged, fully submerged and wet black cotton type of foundation shall also be covered under this.

c) **Dry Fissured Rock**

Limestone, laterite, hard conglomerate or other soft or fissured rock in dry condition which can be quarried or split with crowbars, wedges, pickaxes

etc. However, if required, light blasting may be resorted to for loosening the material but this will not in any way entitle the material to be classified as hard rock.

d) **Wet Fissured Rock**

Above fissured rock, when encountered with subsoil water within the range of foundation depth or land where pumping or bailing out of water is required, shall be treated as wet fissured rock.

e) **Hard Rock**

Any rock excavation, other than specified under fissured rock above, for which blasting, drilling, chiseling is required. The unit rate quoted for hard rock excavation shall be inclusive of all costs for such drilling (including drilling required for anchoring), chiseling and blasting, etc.

1.7.1.5 No extra payment shall be admitted for the removal of fallen earth into a pit or borehole once excavated.

1.7.1.6 Where rock is encountered, the holes for tower footings shall preferably be drilled. Blasting where resorted to as an economy measure, shall be done with utmost care to minimise fracturing rock and using extra concrete for filling the blasted area. All necessary precautions for handling and use of blasting materials shall be taken. In case where drilling is done, the stubs may be shortened suitably with the approval of the Employer.

In cases where unnecessarily large quantities are excavated/ blasted for fissured rock/ hard rock, resulting in placement of large volumes of concrete, payment of concrete shall be limited to design volumes of excavation, concreting, reinforcement etc.

In cases where unnecessarily excavation is done beyond foundation depth for normal foundation other than Hard rock, the same shall be filled with additional Plain cement concrete (PCC) corresponding to a 1:3:6 nominal mix without any additional financial implication to Employer. However minimum thickness of PCC above founding level as shown in the construction drawing of foundation shall be provided.

1.7.1.7 The Contractor shall arrange and supply requisite blasting material, and be responsible for its storage and use, without any extra cost to the Employer.

1.7.1.8 Indian Standard IS 3764 shall be followed regarding safety of excavation work.

**1.8 Unit Rates and Measurement for Foundation**

1.8.1 The indicative shape of foundations is enclosed in this Specification. The bidder is required to quote the unit rates for different foundation activity namely,

excavation for different types of soils, concreting, supply and placement of reinforcement steel and stub setting in the BPS.

- 1.8.2 The unit rates of excavation for each type of soil shall include excavation along with all associated activities like shoring, shuttering, dewatering till completion of foundation work stock piling, dressing, back filling of foundations after concreting with excavated/ borrowed earth (irrespective of lead) and consolidation of earth, carriage of surplus earth to the suitable point of disposal as required by the Employer or any other activity required for to completion of foundation work in all respect.

The measurement for excavation shall be made on the basis of design excavation volume arrived at considering dimension of pit leaving 150 mm gap around (except for undercut foundations) the base pad or actually excavated whichever is less and the unit rate of this item as indicated in in the Contract. The payment for excavation shall be made as per actual type of soil encountered at the time of excavation, but the total payment for excavation portion shall not exceed the amount as payable for excavation considering the soil type same as that of foundation classification. The decision of the Employer shall be final and binding with respect to classification of soil and foundations.

- 1.8.3 Form boxes shall be used for casting of foundations (except under cut portion of foundation). The unit rate of concreting shall include the cost of supply, fabrication and placement of form boxes, cement, water, coarse and fine aggregates mixing and placing of concrete, curing of concrete and any other activities related/ required for completion of concreting works of foundation. The payment for this item shall be made as per the actual volumes of concreting completed but limited to design volume based on unit rates indicated in the Contract.

- 1.8.4 The unit rate of 'Reinforcement Steel' shall include supply and placement of reinforcement steel, stirrups, wire for binding the reinforcement, chairs, bolsters and spacers etc. as required to complete the foundation work. The payment of reinforcement steel shall be made based on the working drawing. In case of actual unit weight of the reinforced steel is found less than standard unit weight, but within acceptable tolerance variation as per applicable standard, the same shall be accepted without any compensation/ deduction. However, if unit weight is found to be beyond the negative (-ve) tolerance limits specified in IS, the material shall be rejected. Wastage overlaps, couplers (if provided), spacer bars, chairs, stays, hangers and annealed steel wire etc. shall not be measured for the payment and cost of these items shall be deemed to be included in the rates for reinforcement.

No payment shall be made on account of overlaps for joining the reinforcement in any type of foundations except for Pile & Combined Raft Foundation.

## 1.9 Setting of Stubs

1.9.1 The stubs shall be set correctly and precisely in accordance with approved method at the exact location, alignment and levels with the help of stub setting templates and leveling instruments. Minimum clearance between chimney concrete level and ground level shall be ensured as per foundation drawing. Stubs setting shall be done in the presence of Employer's representative available at site where required and for which adequate advance intimation shall be given to Employer by Contractor. Tolerances as per provisions of IS 5613 shall be allowed for stub setting.

1.9.2 Setting of stub at each location shall be approved by Employer.

1.9.3 Individual Leg stub setting template may also be used by the contractor with prior approval from Employer Site-In-Charge. An indicative drawing for individual leg stub setting template is attached with the specification. Proper care shall be taken by the contractor for accurate setting & alignment of stub levels

1.9.4 Alternatively, props may be used with complete accuracy and high skilled supervision, subject to prior approval from Employer/ Site-In-Charge. No recovery shall be made on account of using Props for stub setting.

### 1.9.5 Stub Setting Templates/ Props

1.9.5.1 Stub setting templates shall be arranged by the Contractor at his own cost for all heights of towers. Stub templates shall be of adjustable type. The Contractor shall also arrange for props for setting of stubs at specific locations where use of prop is approved by the Employer. Stub templates/ props should be painted.

1.9.5.2 The Contractor shall deploy sufficient number of templates/ props for timely completion of the line without any extra cost to Employer.

1.9.5.3 However, the number of templates to be deployed shall depend upon type of terrain condition, number of types of towers etc. Hence, the quantity of template to be deployed for timely completion of the line shall be finalized in consultation with Site-In-Charge without any extra cost to the Employer.

The number of sets of props (if permitted) to be arranged, will depend as per actual site condition and completion schedule of line.

1.9.5.4 One set of each type of stub setting template/ props (if used) shall be supplied to the Employer, on completion of the project, at no extra cost to Employer.

## 1.10 Mixing, Placing and Compacting of Concrete

1.10.1 The concrete shall be mixed in the mechanical mixer. However, in case of difficult terrain, hand mixing may be permitted at the discretion of the Employer. The water for mixing concrete shall be fresh, clean and free from oil, acids and alkalis. Saltish or blackish water shall not be used.

Alternatively, Ready Mix concrete from batching plant as per IS 4925 can also be used with no extra payment and without any recovery. However, cement content shall be as per IS 456, unless otherwise specified herein. The ready-mix concrete shall conform to IS 4926. The selection and use of Materials for the ready-mix concrete shall be in accordance with IS 456. The concrete shall be of M25 grade design mix as per IS 456. The transport of concrete and transportation time shall be as per IS 4926. Record of delivery ticket information as per Annexure-G of IS 4926 has to be maintained.

- 1.10.2 Mixing shall be continued until there is uniform distribution of material and mix is uniform in colour and consistency, but in no case the mixing be carried out for less than two minutes. Normal mixing shall be done close to the foundation but exceptionally, in difficult terrain, the concrete may be mixed at the nearest convenient place. The concrete shall be transported from the place of mixing to the place of final deposit as rapidly as practicable by methods which shall prevent the segregation or loss of any ingredient. The concrete shall be placed and compacted before setting commences.
- 1.10.3 To avoid the possibility of reinforcement rods being exposed due to unevenness of the bottom of the excavated pit, a pad of lean concrete 50 mm thick and corresponding to a 1:3:6 nominal mix shall be provided at the bottom of the pad. The coarse aggregate shall be of 20mm size and shall conform to IS 383.
- 1.10.4 Form boxes shall be used for casting all types of foundations except at an undercut interface for which the adjoining subsurface material shall provide adequate support. Form boxes shall conform to the shape, lines & dimensions of the foundation drawing and shall be constructed so as to be rigid during the placing and compacting of concrete. Contractor shall ensure that Form boxes are in good condition. Repeated use & maintenance of form box shall be as per IS 456 & IS 14687.
- 1.10.5 The concrete shall be laid down in 150mm layers and consolidated well, so that the cement cream works, up to the top and no honey-combing occurs in the concrete. A mechanical vibrator shall be employed for compacting the concrete. However Monolithic casting of foundation must be carried out. However, in case of unavoidable circumstances, a key construction joint can be provided at the chimney-pad interface subject to approval of the Employer or as directed by the Engineer-in-charge. Number of such joints shall be kept minimum. Joints shall be kept as straight as possible & such construction joints should comply with IS 456. There shall not be any construction joint near stub & cleat portion of frustum. However, nothing extra shall be paid to the Contractor for providing such construction joints. For raised chimney, joint in concrete shall be of 3 m in chimney portion if casting of full chimney is not possible in one stretch.
- 1.10.6 After concreting the chimney portion to the required height, in the top 50 mm portion between CL & GL coping shall be done after erection of tower and the top

surface should be finished smooth with a slight slope towards the outer edge for draining rain water.

Further, in case of Wet, Wet cultivated, PS, FS & WBC foundation before coping of chimney top portion, three coats of anti-corrosive paint (As recommended by paint manufacture for structural steel application) of minimum 30-35 microns dry film thickness each shall be applied on the stub in the 50 mm coping portion as well as upto 350 mm above CL portion. Cost of supply and application of anti-corrosive paint shall be deemed to be included in the unit rate of concreting.

1.10.7 Wet locations shall be kept completely dewatered, both during and 24 hours after placing the concrete, without disturbance of the concrete.

1.10.8 If minor defects in concrete surface is found after the form work has been removed, the damage shall be repaired with a rich cement sand mortar to the satisfaction of the Employer before the foundation is back filled.

#### 1.11 **Curing**

The concrete shall be cured by maintaining the concrete wet for a period of at least 10 days after placing. Once the concrete has set for 24 hours the pit may be backfilled with selected moistened soil and well consolidated in layers thereafter both the backfill earth and exposed chimney shall be kept wet for the remainder of the prescribed 10 days. The exposed concrete chimney shall also be kept wet by wrapping gunny bags around it and wetting the bags continuously during the initial 10 days period.

Alternatively, membrane curing may also be carried over all exposed surface of concrete in line with IS 456

#### 1.12 **Backfilling and Removal of Stub Templates**

1.12.1 After opening of formwork and removal of shoring, shuttering etc., backfilling shall be done with the excavated soil, unless it consists of large boulders/ stones, in which case the boulders/ stones shall be broken to a maximum size of 80 mm or disposed-off. At locations, where borrowed earth is required for backfilling, Contractor shall bear the cost of the borrowed earth irrespective of leads & lift.

1.12.2 The backfilling materials shall be clean and free from organic or other foreign materials. The earth shall be deposited in various layers, levelled, wetted if necessary and shall be fully compacted. All excavated earth shall be placed over the filled in pit to allow further settlement, if any, by gravity.

1.12.3 The backfilling and grading shall be carried to an elevation of about 75 mm above the finished ground level to drain out water. After backfilling 50 mm high, earthen embankment (band) will be made along the sides of excavation pits and sufficient water will be poured in the backfilling earth for at least 24 hours. After the pits have been backfilled to full depth the stub template can be removed.

### 1.13 Benching

When the line passes through hilly/ undulated terrain, levelling the ground may be required for casting of tower footings. All such activities shall be termed benching and shall include cutting of excess earth and removing the same to a suitable point of disposal as required by Employer. Benching shall be resorted to only after approval from Employer. Volume of the earth to be cut shall be measured before cutting and approved by Employer for payment purposes. Further, to minimise benching, unequal leg extensions/ raised chimney shall be considered and provided if found economical. The proposal shall be submitted by the Contractor with detailed justification to the Employer.

### 1.14 Protection of Tower and Tower Footing

- 1.14.1 Tower shall be spotted such that the quantities of revetment are optimum. For tower locations in undulated terrain such as hill/ mountain slopes, options like use of unequal leg extensions for towers, unequal chimney extensions etc. shall be explored by the contractor for optimizing the need for revetment & benching.
- 1.14.2 The work shall include all necessary stone revetments, concreting and earth filling above ground level, the clearing from site of all surplus excavated soil, special measures for protection of foundation close to or in nalas, river bank / bed, undulated terrain, protection of uphill/ downhill slopes required for protection of tower etc., including suitable revetment or galvanised wire netting and meshing packed with boulders. The top cover of stone revetment shall be sealed with 1:2:4 nominal mix concrete. Contractor shall recommend protection at such locations wherever required. Details of protection of tower/ tower footing are given in drawing enclosed with these specifications for reference purpose only.
- 1.14.3 Tower footings shall generally be backfilled using soil excavated at site unless unsuitable for backfilling. In the latter case, backfilling shall be done with borrowed earth of suitable quality irrespective of leads and lift. The unit rate for backfilling quoted in BPS shall include the required lead and consolidation and leveling of earth after backfilling.
- 1.14.4 The provisional quantities for protection work of foundations are furnished in BPS. The unit rates shall also be applicable for any quantity variations during execution. The same unit rates shall hold good for protection work carried out on down hills or up hills slopes applicable for the tower locations.
- 1.14.5 The unit rate for random rubble masonry revetment quoted in price schedule shall also include excavation & (1:5) random masonry. For payment purposes the volume of random rubble masonry revetment shall be measured from bottom of RRM to bottom of M15 sealing and paid at the unit rates indicated in the Contract.

No extra payment shall be made for allied works such as excavation for revetment, packed stone at head of weep holes etc. However, no deduction shall be made for the volume enclosed by weep holes.

- 1.14.6 For some of the locations in nalas, river bed or undulated terrain etc., boulders of minimum. 150mm size bounded and packed in galvanised wire net/ mesh of 8 SWG wire and 10000 square mm (maximum) mesh are to be provided. These stones shall be provided in crates size of 2.0 m x 2.0 m or as deemed suitable for a particular location. Measurement shall be taken in cubic meters and 15% deduction will be made for void from cage/ stack measurements.
- 1.15 After completion of foundation, stub levels, back to back dimensions, diagonal dimensions etc. shall be measured jointly by the Engineer of Contractor and Employer before taking up erection of tower and same shall be recorded for future reference. In case of any deviations beyond permissible limits as per IS 5613, the foundation shall be rectified or re-casted by the contractor at his own cost.